

Friday, March 09, 2007

Vitamide® AS10VN1357/1F

Jackdaw Polymers - Polyamide 66

Unit System:

Actions

Legend ([Open](#))

General Information

General

Material Status	• Commercial: Active
Availability	• Europe
Test Standards Available	• ASTM • ISO
Appearance	• Natural Color
Forms	• Pellets

ASTM and ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density -Specific Gravity	1.13	sp gr 23/23°C	ASTM D792
Density	1.13	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
(Flow)	1.5	%	
(Transverse)	1.5	%	
Water Absorption @ 24 hrs (73 °F)	1.5	%	ASTM D570
Water Absorption 24h/23C	1.5	%	ISO 62
Water Absorption @ Sat.	8.0	%	ASTM D570
Water Absorption Sat/23C	8.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	435000	psi	ASTM D638
Tensile Modulus	435000	psi	ISO 527-1, -2
Tensile Strength @ Break	10900	psi	ASTM D638
Tensile Stress at Break	10900	psi	ISO 527-1, -2
Tensile Elongation @ Brk	30	%	ASTM D638
Tensile Strain at Break	30	%	ISO 527-1, -2
Flexural Modulus	406000	psi	ASTM D790
Flexural Modulus	406000	psi	ISO 178
Flexural Strength	15200	psi	ISO 178
Flexural Strength @ Break	15200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ²	2.38	ft·lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
DTUL @66psi - Unannealed	374	°F	ASTM D648

HDT B (0.45 MPa) Unannealed	374 °F	ISO 75B-1, -2
DTUL @264psi - Unannealed	158 °F	ASTM D648
HDT A (1.80 MPa) Unannealed	158 °F	ISO 75A-1, -2
Vicat Softening Temperature (B50(50°C/h 50N))	446 °F	ISO 306
Melting Point	500 °F	
CLTE, Flow	0.000039 in/in/°F	ASTM D696

Electrical	Nominal Value Unit	Test Method
Volume Resistivity	1.0E+15 ohm-cm	ASTM D257
Volume Resistivity	1.0E+15 ohm-cm	IEC 60093
Dielectric Strength	686 V/mil	ASTM D149
Comp Track Index (A)	600 V	IEC 60112
Electric Strength	690 V/mil	IEC 60243-1
Flammability	Nominal Value Unit	Test Method
Flame Rating - UL	V-2	UL 94
Limiting Oxygen Index	27 %	ASTM D2863
Limiting Oxygen Index	27 %	ISO 4589-1, -2

Additional Properties

Comparative Tracking Index, ASTM D3638, Solution A: 600 V

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 1, Notch A



Copyright © 2007 [IDES - The Plastics Web®](http://www.ides.com)

The information presented on this data sheet was acquired by IDES from various sources, including the producer of the material and recognized testing agencies. In some cases, material updates have been integrated directly into the IDES Plastics Database by the material producer utilizing the Data Maintenance Tool. IDES makes substantial efforts to assure the accuracy of this data. However, IDES assumes no responsibility for the data values and urges that upon final material selection, data points are validated with the manufacturer.